



Recommendations for Application

STRUKTOL® LR 447 is a solvent-free release agent with very good release and gliding properties for many polymers.

STRUKTOL® LR 447 effectively reduces stickiness of NR-latex films in the wet and dry state. Additionally, STRUKTOL® LR 447 considerably improves the lubricity of wet polymeric films.

STRUKTOL® LR 447 may be diluted in any ratio with deionized water.

Dosage

1 – 10 %



Disclaimer:

This publication is not a specification and does not contain any instruction manual or operating guidelines. It is provided for information purposes only and without any responsibility. Schill + Seilacher "Struktol" makes no representations about the accuracy, reliability or completeness of the information in this publication. We reserve the right to revise our not specified products and the information at any time without notice. The information in this publication is based on the present state of our knowledge and experience and serves the general description of our products and their possible applications. Our technical advice and recommendations, whether verbal, in writing or by way of trials, do not absolve the recipient, on account of the many outside influences which may affect the product use and application, from their own testing and trials. A legally binding assurance based on the information contained herein regarding particular properties or the suitability for definite customer applications cannot be derived from our information.

In accordance with the provisions of our General Terms and Conditions of Sale and Delivery, which can be accessed under www.struktol.de, Schill+Seilacher "Struktol" excludes liability for slightly negligent breaches of obligations arising from the use of the information contained in this publication, provided that they do not relate to damage from injury to life, limb or health or guarantees or claims under the Product Liability Act are affected. Furthermore, the liability for the breach of obligations, the fulfilment of which is essential for the proper execution of the contract and on the observance of which the customer may regularly rely, remains unaffected. The same applies to breaches of duty by our agents.

This technical datasheet is created automatically and is valid without signature.

