



Schill+Seilacher

Technical Data Sheet

STRUKTOL® ZEH

Activator for Natural Rubber

Composition

Zinc-2-ethylhexanoate

Properties

Appearance		high viscous liquid
Density	[kg/m ³]	1180
Viscosity at 25 °C	[mPa·s]	max. 7000
Zinc content	[%]	22.9
Physiological behaviour		refer to safety data sheet
Storage stability		at least 24 months under normal storage conditions
Packing		200 kg drums

The data given are typical values which are not intended for use in preparing specifications. For test methods refer to the corresponding supplement.



Bank: Commerzbank AG, Hamburg, BIC: COBA DE FFXX
 IBAN: DE07 2004 0000 0613 1254 00
 Bank: DZ Bank, Hamburg, BIC: GENO DE FF20
 IBAN: DE74 2006 0000 0000 1461 68
 Bank: Commerzbank AG, Hamburg, BIC DRES DE FF20
 IBAN: DE45 2008 0000 0275 0570 00
 Bank: Svenska Handelsbanken AB (publ), Frankfurt, BIC HAND DE FFXXX
 IBAN: DE31 5142 0600 0012 4460 01

Sitz der Gesellschaft:
 Hamburg
 Registergericht:
 Handelsregister Hamburg
 HRB 112163
 ID-Nr. DE 813088647
 Steuer-Nr. 46/757/00201
 Gesellschaft mit
 beschränkter Haftung

Hausanschrift/Address:
 Moorfleeter Straße 28
 22113 Hamburg
 Postfach: 74 07 60
 22097 Hamburg, Germany
 Geschäftsführer:
 Dr. Rüdiger Ackermann

Telefon: 4.19-1-01-01-(5)
 + 49 40 733 62-0
 Fax:
 Verkauf: + 49 40 733 62-194
 Einkauf: + 49 40 733 62-39222
 Zentrale: + 49 40 733 62-194
 Geschäftsleitung: + 49 40 733 62-124
 E-Mail: info@struktol.de
 Internet: www.struktol.de

**Schill+Seilacher****Recommendations for Application**

STRUKTOL® ZEH a rubber-soluble zinc soap, is an activator for natural rubber. It is used instead of stearic acid and reduces in an excellent way stress relaxation and primary creep of NR-vulcanizates, especially in combination with soluble EV-systems.

STRUKTOL® ZEH can be used for masticating natural rubber like other soluble zinc soaps.

STRUKTOL® ZEH can partly replace stearic acid also in synthetic rubber like SBR and NBR. Constant physical values such as tensile strength and elasticity can be achieved caused by the good dispersion of the soluble activator.

STRUKTOL® ZEH should not be used in polychloroprene or other halogen containing polymers because of its influence on scorch.

Dosage

1 - 3 phr

The suggestions for application and usage of our products as well as possible proposed formulations are meant to advise only to the best of our knowledge. This information is without obligation and does not release customers from their own testings to ensure suitability for intended processes and use. Liability is only accepted in case of intention or gross negligence. Liability for any defects caused by minor negligence are not accepted. Each producer is responsible and liable to observe legislation and patent rights of third parties.

This new leaflet replaces all previously printed documentation.

Alterations reserved. 07/2018

Schill + Seilacher "Struktol" GmbH Moorfleeter Straße 28 22113 Hamburg Germany
Phone: +49 40 73362-0 Fax: +49 40 73362-194 E-Mail: info@struktol.de