



# Schill+Seilacher

Technical Data Sheet

## STRUKTOL® TS 35-DL

Tackifier and Softener

### Composition

Aliphatic-aromatic soft resin	67 %
Silica	33 %

### Properties

Appearance		light crumbly powder
Density	[kg/m <sup>3</sup> ]	1200
Bulk density	[kg/m <sup>3</sup> ]	600
Ash content	[%]	31
Physiological behaviour		refer to safety data sheet
Storage stability		at least 24 months under normal storage conditions
Packing		20 kg bags

The data given are typical values which are not intended for use in preparing specifications. For test methods refer to the corresponding supplement.



Bank: Commerzbank AG, Hamburg, BIC: COBA DE FFXXX  
 IBAN: DE07 2004 0000 0613 1254 00  
 Bank: DZ Bank, Hamburg, BIC: GENO DE FF200  
 IBAN: DE74 2006 0000 0000 1461 68  
 Bank: Commerzbank AG, Hamburg, BIC DRES DE FF200  
 IBAN: DE45 2008 0000 0275 0570 00  
 Bank: Svenska Handelsbanken AB (publ), Frankfurt, BIC HAND DE FFXXX  
 IBAN: DE31 5142 0600 0012 4460 01

Sitz der Gesellschaft:  
 Hamburg  
 Registergericht:  
 Handelsregister Hamburg  
 HRB 112163  
 ID-Nr. DE 813088647  
 Steuer-Nr. 46/757/00201  
 Gesellschaft mit  
 beschränkter Haftung

Hausanschrift/Address:  
 Moorfleeter Straße 28  
 22113 Hamburg  
 Postfach: 74 07 60  
 22097 Hamburg, Germany  
 Geschäftsführer:  
 Dr. Rüdiger Ackermann

Telefon: 4.19-1-01-01-(5)  
 + 49 40 733 62-0  
 Fax:  
 Verkauf: + 49 40 733 62-194  
 Einkauf: + 49 40 733 62-39222  
 Zentrale: + 49 40 733 62-194  
 Geschäftsleitung: + 49 40 733 62-124  
 E-Mail: info@struktol.de  
 Internet: www.struktol.de

**Schill+Seilacher**

## Recommendations of Application

STRUKTOL TS 35-DL is the Dry Liquid form of the highly viscous resin. As free-flowing powder it offers improved handling over the high viscosity product STRUKTOL TS 35.

STRUKTOL® TS 35-DL contains a resinous plasticizer which significantly increases the low green tack of synthetic rubber compounds, while the storage stability and cure rate of those compounds are not influenced.

The processability of compounds is improved by the addition of STRUKTOL® TS 35-DL. Furthermore, a good dispersion of carbon black and mineral fillers is achieved.

The physical properties vary only within the generally accepted rate for plasticizers. The low temperature flexibility is not influenced by STRUKTOL® TS 35-DL compared to most other synthetic plasticizers.

Having a good resistance to extractability by aliphatic hydrocarbons and mineral oils STRUKTOL® TS 35-DL is recommended for oil-resistant compounds.

## Dosage

5 - 25 phr.

The suggestions for application and usage of our products as well as possible proposed formulations are meant to advise only to the best of our knowledge. This information is without obligation and does not release customers from their own testings to ensure suitability for intended processes and use. Liability is only accepted in case of intention or gross negligence. Liability for any defects caused by minor negligence are not accepted. Each producer is responsible and liable to observe legislation and patent rights of third parties. This new leaflet replaces all previously printed documentation. Alterations reserved. 07/2018

Schill + Seilacher "Struktol" GmbH Moorfleeter Straße 28 22113 Hamburg Germany  
Phone: +49 40 73362-0 Fax: +49 40 73362-194 E-Mail: info@struktol.de