



## **Technical Data Sheet**

# STRUKTOL® HT 207

Processing Additive for Rubber Processing

### Composition

Mixture of soaps and fatty acid esters

## **Properties**

Appearance Beige to pale yellow pastilles

Density [kg/m³] 1060

Bulk density [kg/m³] 600

Melting point [°C] 65

Physiological behaviour Refer to safety data sheet

Storage stability At least 24 months under normal storage

conditions (store in a dry place)

Packaging 20 kg bags







#### **Recommendations for Application**

STRUKTOL® HT 207 is a processing additive for applications in natural and synthetic rubber.

As a blend of relatively polar fatty acid derivatives STRUKTOL® HT 207 acts in non-polar elastomers predominantly as an external lubricant and release agent, since it has the tendency to accumulate at interfaces, this resulting in reduced friction and tackiness. In practice, this effect shows as improved extrusion rate and reduced mill roll sticking.

Due to its specific composition the product softens readily and can easily be incorporated at temperatures above 65  $^{\circ}$ C.

In polar rubbers such as NBR the internal lubrication is to the fore resulting in a reduction of compound viscosity.

Due to its pronounced surfactant character STRUKTOL® HT 207 is strongly adsorbed to fillers thus supporting filler dispersion and breaking up of filler agglomerates. This does not only lead to improved compound homogeneity but also to reduced compound viscosity. The effect is naturally strong with the polar mineral fillers.

Since STRUKTOL® HT 207 has a certain alkalinity, it has an activating effect upon the sulphur cure. When too fast scorch is observed in individual cases, addition of a suitable retarder (e.g., N-Cyclohexylthiophthalimide) should be taken into consideration.

STRUKTOL® HT 207 has particularly been developed from environmental aspects and contains no heavy metals. In many applications it can replace zinc soaps previously used as processing additives and thus it is an important contribution to the currently demanded reduction of the zinc content of rubber compounds.

#### Dosage

2 - 5 phr







#### Disclaimer:

This publication is not a specification and does not contain any instruction manual or operating guidelines. It is provided for information purposes only and without any responsibility. Schill + Seilacher "Struktol" makes no representations about the accuracy, reliability or completeness of the information in this publication. We reserve the right to revise our not specified products and the information at any time without notice. The information in this publication is based on the present state of our knowledge and experience and serves the general description of our products and their possible applications. Our technical advice and recommendations, whether verbal, in writing or by way of trials, do not absolve the recipient, on account of the many outside influences which may affect the product use and application, from their own testing and trials. A legally binding assurance based on the information contained herein regarding particular properties or the suitability for definite customer applications cannot be derived from our information.

In accordance with the provisions of our General Terms and Conditions of Sale and Delivery, which can be accessed under <a href="www.struktol.de">www.struktol.de</a>. Schill+Seilacher "Struktol" excludes liability for slightly negligent breaches of obligations arising from the use of the information contained in this publication, provided that they do not relate to damage from injury to life, limb or health or guarantees or claims under the Product Liability Act are affected. Furthermore, the liability for the breach of obligations, the fulfilment of which is essential for the proper execution of the contract and on the observance of which the customer may regularly rely, remains unaffected. The same applies to breaches of duty by our agents.

This technical datasheet is created automatically and is valid without signature.

