



Schill+Seilacher

Technical Data Sheet

STRUKTOL® WB 700

Metal Oxide Preparation

Composition

Zinc oxide	91 %
Dispersing agent	9 %

Properties

Appearance		powder
Density	[kg/m ³]	3800
Bulk density	[kg/m ³]	1200
Ash content	[%]	90.5
Physiological behaviour		refer to safety data sheet
Storage stability		at least 18 months under normal storage conditions
Packing		20 kg bags
Factor of dosage		1.1

The data given are typical values which are not intended for use in preparing specifications. For test methods refer to the corresponding supplement.



Bank: Commerzbank AG, Hamburg, BIC: COBA DE FFXXX
 IBAN: DE07 2004 0000 0613 1254 00
 Bank: DZ Bank, Hamburg, BIC: GENO DE FF200
 IBAN: DE74 2006 0000 0000 1461 68
 Bank: Commerzbank AG, Hamburg, BIC DRES DE FF200
 IBAN: DE45 2008 0000 0275 0570 00
 Bank: Svenska Handelsbanken AB (publ), Frankfurt, BIC HAND DE FFXXX
 IBAN: DE31 5142 0600 0012 4460 01

Sitz der Gesellschaft:
 Hamburg
 Registergericht:
 Handelsregister Hamburg
 HRB 112163
 ID-Nr. DE 813088647
 Steuer-Nr. 46/757/00201
 Gesellschaft mit
 beschränkter Haftung

Hausanschrift/Address:
 Moorfleeter Straße 28
 22113 Hamburg
 Postfach: 74 07 60
 22097 Hamburg, Germany
 Geschäftsführer:
 Dr. Rüdiger Ackermann

Telefon:
 Fax:
 Verkauf:
 Einkauf:
 Zentrale:
 Geschäftsleitung:
 E-Mail:
 Internet:

4.19-1-01-01-(5)
 + 49 40 733 62-0
 + 49 40 733 62-194
 + 49 40 733 62-39222
 + 49 40 733 62-194
 + 49 40 733 62-124
 info@struktol.de
 www.struktol.de

**Schill+Seilacher**

Recommendations of Application

STRUKTOL® WB 700 may be used in rubber compounds where the dispersion of untreated zinc oxide gives rise to problems. The product acts to reduce sticking to the rotor blades and mill rolls.

STRUKTOL® WB 700 is a non-dusting powder and is preferably used owing to its zinc oxide content of 91 % where high amounts of dispersing agents are undesirable.

The suggestions for application and usage of our products as well as possible proposed formulations are meant to advise only to the best of our knowledge. This information is without obligation and does not release customers from their own testings to ensure suitability for intended processes and use. Liability is only accepted in case of intention or gross negligence. Liability for any defects caused by minor negligence are not accepted. Each producer is responsible and liable to observe legislation and patent rights of third parties.

This new leaflet replaces all previously printed documentation.
Alterations reserved. 07/2018

Schill + Seilacher "Struktol" GmbH Moorfleeter Straße 28 22113 Hamburg Germany
Phone: +49 40 73362-0 Fax: +49 40 73362-194 E-Mail: info@struktol.de