

## Technical Data Sheet

**STRUKTOL® LR 184**

Liquid Parting Agent for Uncured Rubber Sheets

**Composition**

Zinc-free, aqueous dispersion of inorganic fillers and processing additives

**Properties**

Appearance		whitish liquid
Solids content	[%]	31
Density	[kg/m <sup>3</sup> ]	1200
pH value		8
Physiological behaviour		refer to safety data sheet
Storage stability		at least 6 months when stored in a closed container. Product should be thoroughly stirred before application to redisperse settled solids. transport and storage at temperatures above 6 °C is imperative
Packing		125 kg and 220 kg drums; 1000 kg container

The data given are typical values which are not intended for use in preparing specifications. For test methods refer to the corresponding supplement.



## **Recommendations for application**

STRUKTOL LR 184 is a liquid parting agent suited for use in batch-off equipment for uncured rubber sheets.

It is applied by dipping or spraying.

STRUKTOL LR 184 complies with 21 CFR 177.2600 (FDA).

## **Recommended concentrations**

Dilute to 5 to 7.5 % solids concentration (add 3 - 5 parts of water to 1 part STRUKTOL LR 184)

Periodic gentle agitation will easily re-suspend any settled material.

The suggestions for application and usage of our products as well as possible proposed formulations are meant to advise only to the best of our knowledge. This information is without obligation and does not release customers from their own testings to ensure suitability for intended processes and use. Liability is only accepted in case of intention or gross negligence. Liability for any defects caused by minor negligence are not accepted. Each producer is responsible and liable to observe legislation and patent rights of third parties.

This new leaflet replaces all previously printed documentation.

Alterations reserved. 29/2004

Schill + Seilacher "Struktol" GmbH Moorfleeter Straße 28 22113 Hamburg Germany  
Phone: +49 40 73362-0 Fax: +49 40 73362-194 E-Mail: [info@struktol.de](mailto:info@struktol.de)